Elastopatch 300 Patching and Leveling Compound



Properties / Specifications

Color: Light grey

Set time initial: 2 hours **Set time final:** 18 hours

(ASTM C 266)

Compressive strength:

1 day: 200 psi 7 days: 1000 psi (ASTM C 109)

Abrasion: 0.80% (ASTM C 4060)

Adhesion: 7 day cure (concrete) 55 (ASTM C 297)

Kit Yield

Approximately 0.30 cubic feet - enough to cover 3.5 square feet to a depth of one inch.

Kit Contents

5 gallon pail
1 gallon Elastopatch
1 packet Elastopatch
Accelerator
25 lb dry mix
Instructions

Davlin Coatings LLC 700 Allston Way Berkeley Ca 94710 USA (800) 709-5919 www.davlincoatings.com

made in the USA designed by Davlin in California

© 2015 Davlin Coatings

Elastopatch 300 is a resin modified cementitious leveling compound, designed to create auxiliary slope over roofs to divert water flow toward drains, scuppers, or outside edge. The product combines a proprietary blend of cement, aggregates, and liquid emulsions to achieve a workable, easy to use leveling material.

Elastopatch 300 can be installed in a single application, providing a quick and easy way to fill low spots in flat roofs and achieve positive slope to aid in proper drainage. It is excellent for new construction as well as retrofit work, minimizing the removal or addition of other draining/leveling constructs.

Product Weight Chart

Product Thickness	Weight per Square Foot
0.25 inch	2.5 lbs
0.5 inch	5 lbs
0.75 inch	7.5 lbs
1 inch	10 lbs
1.5 inch	15 lbs
2 inch	20 lbs

The information, ratings, and opinions stated above are, to the best of our knowledge, accurate, representing the results of laboratory and field evaluation. It is presented in good faith, to assist the user in determining whether our products are suitable for his/her application. Since the user's application and other requirements are not known by us or are beyond our control, no warranty or guarantee as to results is hereby made or implied by Davlin Coatings, LLC.