

# RESTORE, REJUVENATE,

and Refresh the Color of Your Tile Roof With

# 300 RR TILE RESTORATION





# 300 RR TILE RESTORATION

## PHYSICAL PROPERTIES

<b>COLOR:</b> STANDARD AND CUSTOM COLORS	<b>VOC:</b> <0.37 LB/GAL
<b>COMPONENTS:</b> 1	<b>PERCENT NON VOLATILE:</b> 30%
<b>VISCOSITY:</b> 52-58 KREBS	<b>WEIGHT PER GALLON:</b> 8.5LBS
<b>FLASH POINT (SETA):</b> >215 F	<b>CURING MECHANISM:</b> AIR DRY
<b>COVERAGE PER GALLON:</b> 150SQ/FT	<b>COATS:</b> 1-2
<b>PENETRATION:</b> NO. 52 WHATMAN, INCHES MIN 1	

### Product Description:

300 RR TILE RESTORATION is a waterborne emulsion developed to restore and rejuvenate concrete tiles. It provides weather protection and refreshes color on an old tile roof.

### Product Use:

300 RR TILE RESTORATION is primarily used to restore, rejuvenate, and refurbish the color of old concrete tile roof.

### Product Advantages:

300 RR is easy to apply with airless, roller or brush.  
300 RR is water-based for easy clean-up and low odor.  
Four standard and custom colors

### Packaging:

300 RR TILE RESTORATION is available in one (1) and five (5) gallon pails, 55 gallon drums, and 265 gallon totes.

### Surface Preparation:

All surfaces must be clean, free of dirt, algae, mildew and other contaminants.

### Application Procedure:

Stir 300 RR TILE RESTORATION thoroughly until uniformly blended. Avoid excessive mixing to prevent air entrapment. Thinning is not recommended.

Spray, Brush or Roll saturating entire surface.

Drying time to recoat at 70 °F. 50% RH : 2 hours

Clean equipment with water or water and detergent immediately after use.

### Product Limitations:

Do not apply during or 24 hours preceding inclement weather including rain, fog, mist or freezing temperatures.

Keep Material from freezing

The information, ratings, and opinions stated above are, to the best of our knowledge, accurate, representing the results or laboratory and field evaluation. It is presented in good faith, to assist the user in determining whether our products are suitable for his application. Since the user's application and other requirements are not known by us or are beyond our control, no warranty or guarantee as to results is hereby made or implied by Davlin Coatings LLC.